


Oil★Star® Detonators

A-2B

PRODUCT INFORMATION BROCHURE

PROPERTIES

A-2B	
Shell Length	32 mm / 1.25 "
Base Charge	5 grains RDX (0.325 gram)
No-Fire Current (approx.) (Based on a constant voltage for 1 minute)	0.2 amperes
All-Fire Current (approx.)	0.8 amperes
Minimum Firing Current (approx.)	0.5 amperes
Leg to Leg Resistance Plus 0.032 for each foot of duplex wire	0.8 ± 0.1 ohm + 0.27/0.32 ohm
High Temperature Performance	1 hr. at 350°F
Pressure Rating per 24 Hours	1 hr. at 100 psi
Electrostatic Sensitivity Energy Value (Double leg to shell capacitor discharge energy level)	78 mJ



ADVANTAGES

- Antistatic sleeve and spark gap protect against static electricity.
- Leg wires are high temperature Teflon insulated 22 gauge four feet long copper leg wires.

STANDARD TECHNICAL DESCRIPTION

Instantaneous RDX detonator



AUSTIN POWDER

Austin Powder Company, 25800 Science Park Drive

Phone: 1-800-321-0752 | Fax: 1-216-464-4418 | Email: info@austinpowder.com | www.austinpowder.com



Oil★Star Detonators

A-2B

STANDARD PACKAGING DETAILS

Oil★Star A-2B detonators are packaged 50 detonators per inner package, 500 detonators per case.

STORAGE

Store in accordance with all applicable local, state, provincial and federal laws.

SHELF LIFE

For optimum accuracy, use within five years from date of manufacture under good storage conditions.

TRANSPORTATION DATA

UN CLASSIFICATION

Shipping Name: Detonators, electric, for blasting

Class & Division: 1.4B

ID Number: UN 0255

US DOT REFERENCE NUMBER

EX-199511002



Disclaimer of Warranties and Limitations of Liabilities: Products described in this bulletin are sold by Austin Powder Company without warranty; express, implied or statutory or as to MERCHANTABILITY, except as expressly stated in Austin Powder's straight bill of lading. Under no circumstances shall seller be liable for loss of anticipated profits, consequential damages or incidental damages.

© 2020 Austin Powder Company. All rights reserved.

For more information and service locations in your area, please contact Austin Powder Company's headquarters:



AUSTIN POWDER

Austin Powder Company, 25800 Science Park Drive

Phone: 1-800-321-0752 | Fax: 1-216-464-4418 | Email: info@austinpowder.com | www.austinpowder.com

03/02 | r 01/31/2020