

Austinite^e 3 eco

PRODUCT INFORMATION BROCHURE

Austinite 3 eco consists of porous ammonium nitrate, mineral oil and aluminium, the presence of aluminium enhances heave. Austinite 3 eco is not water resistant and can only be used in dry conditions. Austinite 3 eco is not detonator sensitive.

ADVANTAGES

- High gas volume.
- Very low sensitivity against mechanical and thermal stress.
- Borehole volume is perfectly utilized, therefore high degree of efficiency.
- Perfectly free flowing.
- May be used for pneumatic loading.

PROPERTIES

Properties	Value
Density [g/cm ³]	0.75
Oxygen balance [%] ⁽¹⁾	0.5
Gas Volume [L/kg] ⁽¹⁾	937
Heat of Explosion [kJ/kg] ⁽¹⁾	4,050
RWS [ANFO=100] ⁽¹⁾	110
RBS [ANFO=0.85 g/cm ³] ⁽¹⁾	93
Velocity of detonation [m/s] (confined) ⁽²⁾	3,600

Notes:

⁽¹⁾ Theoretical values based on Austin modeling which assumes ideal detonation. Values calculated with other codes may differ.

⁽²⁾ The velocity of detonation will depend on application, diameter and confinement.



AUSTIN POWDER

Austin Powder GmbH, Weißenbach 16, 8813 St. Lambrecht, Austria
Tel: +43 (0) 3585 2251-0 - Fax: +43 (0) 3585 2414 - office@austinpowder.at

Austinite^e 3 eco

PRODUCT INFORMATION BROCHURE

STANDARD PACKAGING

Available packing sizes	Weight NEQ [kg]
Plastic bag	25.0
Big bag	500.0

Notes: The product is packed according to relevant regulations.

STORAGE

- Lower temperature limit +5 °C.
- Upper temperature limit +30 °C.

USE

- Lower temperature limit -20 °C.
- Upper temperature limit +30 °C.
- Minimum booster APB 450 or emulsion explosive.
- Minimum borehole diameter 50 mm.
- Not for use in hazardous environments where flammable gases or dust may exist.
- We recommend the use of an Emulex 1 or an APB booster charge. The amount of booster explosive in boreholes with a diameter of 50 mm or more should be 6 % minimum of the total explosive mass. In boreholes with a smaller diameter the amount of booster explosive should be 10 % minimum.
- Austin accepts no responsibility for any loss or liability arising from use of the product in ground containing pyritic or other reactive material.

SHELF LIFE

6 months from the date of manufacture.

TRANSPORTATION DATA

Shipping Name: EXPLOSIVE, BLASTING, TYPE B

U.N. Class and Division: 1.1D

U.N. Number: 0082

DISCLAIMER: The data set forth in this Product Information Brochure (PIB) are based on the product test procedures of Austin Powder GmbH in use at the time of publication of this PIB. Specifications, test values and information are exclusively non-binding preliminary information and are not guaranteed; the actual data may differ for various reasons (e.g. temperature, humidity, pressure). Technical inaccuracies or typographical errors and the right to amend the PIB at any time without notice shall be reserved. Austin Powder GmbH does not assume any liability, covenants, guaranties or warranties with respect to the completeness, accuracy, reliability, suitability or availability of the product and the information of the PIB. Any liability for damages of any kind (such as direct or indirect, incidental or consequential damages, losses or expenses), directly or indirectly related for any reason to this PIB or the use of the products is excluded. The customer is (even when making decisions based on the information in the PIB) solely responsible for the proper use of the potentially dangerous products that, accordingly, may only be used by trained personnel and in compliance with applicable law. To the entire legal relationship between their customers and Austin Powder GmbH or Austin Powder Vertriebsgesellschaft m.b.H. their (Austin's) general terms and conditions (they can be downloaded from the homepage www.austinpowder.at) shall apply.



AUSTIN POWDER

Austin Powder GmbH, Weißenbach 16, 8813 St. Lambrecht, Austria
Tel: +43 (0) 3585 2251-0 - Fax: +43 (0) 3585 2414 - office@austinpowder.at

03/2020

